

24.07.2023

Composition of Fly ash

Tudela Fly ash EN 450-1 LOI Cat. B, Fineness Cat.N 0099-CPR-A95-0019

Based on the April 2023 monthly composite sample: 1317

Property		Value	BS EN 450-1 Limit	
Fineness (Residue)	45µm	%	8.9	Declared Value 15% ± 10% (Tested in accordance with BS EN 450-1 cl. 5.3.1)
APD		g/cm ³	2.51	< 200kg/m3 from declared value
28 Day Activity Index - Mar sa	ımple	%	76	>75%
90 Day Activity Index - Feb sa	ımple	%	89	>85%
Sulfate	SO ₃	%	0.89	≤ 3.0%
Loss on Ignition	LOI	%	2.56	≤ 7.0%
Chloride	Cl-	%	0.01	≤ 0.1%
Calcium Oxide	CaO	%	4.90	≤ 10.0%
$SiO_2 + Al_2O_3 + Fe_2O_3$	-	%	84.92	≥ 70.0%
Free Lime	-	%	0.21	≤ 1.5%
Alkalis	Na ₂ Oeq	%	1.19	≤ 5.0%
Declared Mean Alkali Content	Na ₂ Oeq	%	1.50	-
Declared Maximum Chloride Content	Cl ⁻	%	0.05	-

^{*}BS EN 933-10:2009 method replacing the 63 μm sieve with a 45 μm sieve

For and on behalf of Tarmac Cement:

S.Chudley

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM



Conformity of Fly Ash to BS 8500-2: Annex A Tudela EN 450-1 Fly Ash 0099-CPR-A95-0019

Based on the composite samples for the month of: April 2023

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Aberthaw

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	20.8	
28 Day Strength (MPa)	46.7	

Based on equivalent results obtained for the last **12** months, the permitted proportions of combinations conforming to the requirements of Annex A of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	19	35
42,5N	6	28

BS 8500-2 Combination	Fly Ash Content (%)	
Designation	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM

Tarmac Cement and Lime Limited Registered in England and Wales. Company No. 66558



Conformity of Fly Ash to BS 8500-2: Annex A Tudela EN 450-1 Fly Ash 0099-CPR-A95-0019

Based on the composite samples for the month of: April 2023

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Cauldon

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	20.2	
28 Day Strength (MPa)	45.2	

Based on equivalent results obtained for the last **12** months, the permitted proportions of combinations conforming to the requirements of Annex A of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	12	35
42,5N	6	28

BS 8500-2 Combination	Fly Ash Content (%)	
Designation	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM

Tarmac Cement and Lime Limited Registered in England and Wales. Company No. 66558 Registered address: T3 Trinity Park, Bickenhill Lane, Birmingham, B37 7ES



Conformity of Fly Ash to BS 8500-2: Annex A Tudela EN 450-1 Fly Ash 0099-CPR-A95-0019

Based on the composite samples for the month of: April 2023

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Dunbar

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	17.2	
28 Day Strength (MPa)	45.4	

Based on equivalent results obtained for the last **12** months, the permitted proportions of combinations conforming to the requirements of Annex A of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	21	35
42,5N	6	28

BS 8500-2 Combination	Fly Ash Content (%)	
Designation	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM

Tarmac Cement and Lime Limited Registered in England and Wales. Company No. 66558



Conformity of Fly Ash to BS 8500-2: Annex A Tudela EN 450-1 Fly Ash 0099-CPR-A95-0019

Based on the composite samples for the month of: April 2023

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Limerick

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	19.2
28 Day Strength (MPa)	46.3

Based on equivalent results obtained for the last **12** months, the permitted proportions of combinations conforming to the requirements of Annex A of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	8	35
42,5N	6	20

BS 8500-2 Combination	Fly Ash Content (%)	
Designation	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM

Tarmac Cement and Lime Limited Registered in England and Wales. Company No. 66558 Registered address: T3 Trinity Park, Bickenhill Lane, Birmingham, B37 7ES



Conformity of Fly Ash to BS 8500-2: Annex A Tudela EN 450-1 Fly Ash 0099-CPR-A95-0019

Based on the composite samples for the month of: April 2023

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Platin

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	19.4
28 Day Strength (MPa)	44.2

Based on equivalent results obtained for the last **12** months, the permitted proportions of combinations conforming to the requirements of Annex A of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	11	35
42,5N	6	22

BS 8500-2 Combination	Fly Ash Content (%)	
Designation	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM

Tarmac Cement and Lime Limited Registered in England and Wales. Company No. 66558



Conformity of Fly Ash to BS 8500-2: Annex A Tudela EN 450-1 Fly Ash 0099-CPR-A95-0019

Based on the composite samples for the month of: April 2023

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Rugby

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	20.4
28 Day Strength (MPa)	48.5

Based on equivalent results obtained for the last **12** months, the permitted proportions of combinations conforming to the requirements of Annex A of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	19	35
42,5N	6	29

BS 8500-2 Combination	Fly Ash Content (%)	
Designation	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM

Tarmac Cement and Lime Limited Registered in England and Wales. Company No. 66558



Conformity of Fly Ash to BS 8500-2: Annex A Tudela EN 450-1 Fly Ash 0099-CPR-A95-0019

Based on the composite samples for the month of: April 2023

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Tunstead

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	18.0
28 Day Strength (MPa)	47.9

Based on equivalent results obtained for the last **12** months, the permitted proportions of combinations conforming to the requirements of Annex A of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	24	35
42,5N	6	35

BS 8500-2 Combination	Fly Ash C	ontent (%)
Designation	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley

National Commercial Technical Manager Tarmac Cement

TARMAC.COM

Tarmac Cement and Lime Limited Registered in England and Wales. Company No. 66558 Registered address: T3 Trinity Park, Bickenhill Lane, Birmingham, B37 7ES